

# VITRETHANE 633



## Two Pack Polyurethane Floor Coating

Technical Data Sheet Number 1008

<b>PRODUCT DESCRIPTION</b>	<p>A &amp; I Coatings <b>VITRETHANE 633</b> is a two pack non-yellowing polyurethane finish, based on reactive acrylic resin cross-linked using aliphatic isocyanate. V633 offers good application properties, fast dry and cures to a hard wearing finish with excellent chemical and graffiti resistance.</p>				
<b>USES &amp; BENEFITS</b>	<ul style="list-style-type: none"> <li>• Seamless flooring</li> <li>• Topcoat for masonry floors and walls</li> <li>• Other substrates which need a non-yellowing tough coating</li> </ul>				
	<p><u>Benefits</u></p> <ol style="list-style-type: none"> <li>1. Very tough and excellent chemical resistance</li> <li>2. Good, flow &amp; levelling</li> <li>3. Low yellowing</li> <li>4. Excellent abrasion resistance</li> </ol>	<p><u>Limitations</u></p> <ol style="list-style-type: none"> <li>1. Solvent based coating with high VOC</li> <li>2. Pigmented gloss coatings not available.</li> </ol>			
<b>PHYSICAL PROPERTIES</b>	Vehicle Type	Polyurethane			
	Hardener	Isocyanate			
	Mixing Ratio	3:1 (Pack A : Pack B) by Volume			
	Pot Life	2 hours approx. @ 20°C			
	Finish	Gloss or Satin			
	Theoretical Coverage	8.4m <sup>2</sup> /Litre/coat at 50µm DFT at 42% solids			
	Volume Solids	40-55% dependent on colour and finish			
	Recommended DFT	Dependant on specific requirements			
	Usual No. of Coats	Dependant on specific requirements			
	Primer Required	Dependant on substrate. (A & I Coatings staff can advise on the most appropriate primer coat for a specific task)			
	Colour	Clear gloss and satin and various colours in satin			
	Product Weight	0.97 – 1.42 Kg/Litre(Pack A); 1.06 Kg/Litre(Pack B)			
<b>ENGINEERING DATA</b>	Abrasion Resistance	Excellent resistance to scrubbing and wet and dry sand abrasion			
	Flexibility	Good			
	Bacterial Resistance	Excellent			
	Chemical Resistance	Excellent resistance to a wide range of inorganic and inorganic acids. Good resistance to alkalis			
	Graffiti Resistance	Most graffiti damage removed with suitable graffiti remover			
	Dry Heat Resistance	120°C			
	Solvent Resistance	Excellent			
	Durability	Non yellowing and good gloss retention			
<b>CURING DATA</b>	Substrate Temp.(°C)	Touch Dry	Dry to Handle	Full Cure	Recoat Min
	15 °C				
	25 °C	45 Min	6 Hrs	7 Days	4 Hrs
	35 °C				
	Note	Dry to withstand light traffic after overnight cure. Progressively cures over 7 days.			

APPLICATION DATA	Mixing	Thoroughly mix Pack A & Pack B with hand or mechanical stirrer before and after mixing together.
	Application	Roller, airless, air assisted airless, air atomisation.
	Cleaning	V102 Cleaning Solvent.
	Thinning	Use V111 Medium Thinners.
	Typical Specification	<u>Concrete floor coating:</u> First coat (primer): E4110 Two Pack Solvent Free Epoxy Coating at 150µm DFT. Second coat (Topcoat): V633 Exterior Urethane at 75µm DFT.
SURFACE PREPARATION	All Surfaces	All surfaces to be structurally sound and free of contamination, particularly salt deposits. Loose or flaking paint must be removed by abrasive blast cleaning, power tool cleaning or sanding. Oil, grease, dirt etc. must be removed with detergent and water blasting in accordance with AS 1627.1.
	Concrete	Allow new concrete surfaces to cure for a minimum of 28 days before painting. Surface to be painted should be free from oil, grease etc Contact A & I Coatings team for preparation details & primer specifications.
	Aluminium, Galvanised Steel & Zincalume	Remove oil and excess grease with mild detergent or with sugar soap. Slightly roughen the surface with the help of sanding or light whip blasting with a non metallic abrasive. Apply suitable primer according to specification.
	Repaints	All surfaces should be free from oil, grease, loose paint and other contaminants. Though Vitrethane 633 may give good adhesion, a test patch is always necessary before use.
WORK STOPPAGES	General	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with A & I Coatings recommended cleaner. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.
	Clean Up	Clean all equipment after use with A & I Coatings recommended cleaner. It is good work practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, (including delays).
PACKING & STORAGE	Packing	Available in 10L kits. For availability of other sizes, contact A & I Coatings.
	Storage	12 months if stored in sealed containers away from heat & moisture. Subject to re-inspection thereafter.
HEALTH & SAFETY	All applicable statutory regulations must be observed in the application of this product. Users must first read the Material Safety Data Sheet for Vitrethane 633. Users should familiarise themselves with all the safety aspects of the product prior to usage. Please ensure the current Technical Data Sheet is consulted prior to specification or application of A & I Coatings products. If the surface intended to be painted differs from the specification, please consult the A & I Coatings Technical team on 1800 819 585.	

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. Note: The figures quoted for pot life and drying/curing times are not definitive. They are dependent on onsite conditions, such as volume of material mixed, ambient and substrate temperatures, weather and ventilation. **DISCLAIMER** Since the use and application of this product is beyond our control, we cannot be held responsible for product field performance. The information presented above is the result of our considerable experience with this product but is not to be construed as a performance warranty. For additional information, phone our Customer Service Centre on 1800 819 585.

March 2021 - THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED.